



UAB Nepriklausomi tyrimai
K. Donelaičio g. 62
Kaunas LT-44248

Lydinio tyrimo rezultatai

XL3-30417

Reading No 21
Mode ALLOY
Time 2008-04-03 11:25
Duration 30.14
Alloy1 304SS : 0.07
SAMPLE 1
TYPE vamzdis didelis
INSPECTOR
SURFACE Nenusveistas
COMPANY

	%	±	Error
Mo	0.169	±	0.007
Cu	0.441	±	0.053
Ni	8.529	±	0.166
Co	0.293	±	0.138
Fe	70.848	±	0.256
Mn	1.305	±	0.113
Cr	18.039	±	0.152
V	0.159	±	0.047

Atliko: Saulius Burinskas _____